

ARA-1 Product Data Sheet



Description and Physical Properties

ARA-1 (Asphalt Recycling Agent) is an anionic water-based emulsion designed to rejuvenate aged asphalt pavements. The emulsion contains special oils to soften oxidized asphalt surfaces.

Physical Properties:

- C.A.S. Number: 8052-42-4
- Boiling Point (F): 212°F
- Specific Gravity (H₂O=1): 1.01
- Percent Volatile: 0
- Solubility In Water: Soluble
- Appearance and Odor: Light Brown Liquid, Faint Petroleum Odor
- Flammability: Non-flammable in water-based state

Recommended Use

ARA-1 may be applied to the surface with well-calibrated distributors, or it can be used in hot in-place recycling. The distributor nozzles and spray bar should be sized and set to deliver the desired shot rate. The shot rate should be determined by the conditions of the existing pavement. The air and pavement temperatures should be sufficiently high to allow the emulsion to fully cure. ARA-1 should not be applied during rain or imminent threat of rain.

Storage and Handling

The water-based emulsion should not be exposed to overheating. The anionic emulsion is a chemically stabilized system, so care should be taken not to upset the chemical balance with contamination by chemicals, over-exposure to air, or adverse mechanical or thermal conditions. Before being filled, tanks and trucks should be examined for possible contaminants. Recommended use and storage temperatures are given in the table.

Recommended Temperatures	Min	Max
Storage	50°F	140°F
Application	50°F	130°F

Martin Asphalt Quality

Through Martin Asphalt, you get **Everything Asphalt**—a full range of products. In addition, you receive technical assistance in selecting the right materials and application. The company's AASHTO Certified Laboratory makes sure the products meet your specifications. And your products are delivered both on spec and on time via Martin's Gulf Coast network of production plants, storage facilities and transportation fleet including ocean-going and inland barges, rail cars and tanker trucks. For more information, contact us.

www.MartinAsphalt.com

EVERYTHING ASPHALT

800-662-0987

Product Data Sheet - ARA-1 doc rev. 12/18/06